

Product Description

Akona® Concrete Resurfacer is a special acrylic polymer-modified cement used to resurface spalled and/or damaged interior and exterior concrete surfaces such as steps, patios, garage floors, and sidewalks. Akona® Concrete Resurfacer develops a tough bond and dries to a concrete gray color. It may be trowel or broom finished.

When/Where to Use

- Interior / exterior concrete
- Steps, patios, garage floors
- Renew concrete surfaces

Advantages

- Polymer modified
- Trowel or broom
- Just add water mix and use
- Add water, mix and use

Available Sizes:

10lb. bag and 25lb. bag


Coverage

1 lb. per 1 square foot at 1/8" thick

Preparation:

Remove all loose or unsound materials. Thoroughly clean surface with Akona® Fast-Acting Liquid Concrete Cleaner to remove dirt, dust, grease or other contaminants before patching, topping, or placing overlays. Pressure cleaning with a concrete cleaner is advisable. All cracks or depressions more than 1/8" deep must be repaired with Akona® Vinyl Cement Patch three days prior to resurfacing. Smooth troweled or dense concrete surfaces must be etched or roughened to ensure proper bond adhesion. PRE-WET

Helpful Items:



SURFACE JUST PRIOR TO APPLICATION OF PRODUCT WITH NO RESIDUAL WATER POOLING.

Mixing

Add approximately 1 ½ pints of clean, cool water per 10 pounds of powder. Always add powder to liquid to avoid lumps. Mix to a uniform consistency by hand or use a mechanical mixer until a stiff, pourable consistency is reached. Excessive additional water will reduce adhesion and long term durability of resurfacer. Avoid high speed mechanical mixing which can entrap air into the mixture. Do not use any additives other than water. Mix only the quantity that can be applied within 20 minutes.

Application

For best results, do not apply when temperatures drop below 40° F within 48 hours of application. Do not apply in direct sunlight or hot, windy days. Apply to a thickness of 1/8" to 3/16". Surface must be completely dampened with no pooling water remaining. Spread evenly over surface with a flat trowel or squeegee applying some pressure to ensure proper bond. Wetting the trowel blade will aid in refinishing larger areas. Do not apply over expansion joints. Akona® Concrete Resurfacer develops initial set in approximately 10-20 minutes depending on temperature and humidity. Complete troweling or broom finish as soon as possible. Allow to set at least 4 hours before exposure to rainfall. Keep traffic off of surface for a minimum of 12 hours. If desired, seal with either Akona® Water-Based Surface Concrete Sealer or Akona® Penetrating Concrete & Paving Stone Sealer after 7 days. Clean up with soap and warm water as soon as application is completed.

Clean Up

Typically water will satisfactorily clean tools after using Polymer Modified Concrete Resurfacer. If the material has begun to harden, warm soapy water may



be helpful for cleaning hands and tools.

Warranty:

Seller warrants that its product will conform to and perform in accordance with the product specifications. The foregoing warranty is in lieu of all other warranties, express or implied, including, but not limited to, those including merchantability and fitness for a particular purpose. Because of the difficulty in ascertaining and measuring damages hereunder, it is agreed that, seller's liability to the buyer at no point for any particular project shall exceed the total purchase price of said product.

WARNING: INJURIOUS TO EYES!

KEEP OUT OF REACH OF CHILDREN!

PRECAUTIONS:

Avoid contact with eyes and skin. If contact with eyes occurs, flood eyes repeatedly with clean water and see a physician immediately. Do not rub eyes. Wash hands thoroughly after handling or before eating with warm, soapy water. Do not take internally. Keep out of reach of children.

